

## DERCOLYTE LTG

DERCOLYTE LTG is produced from the polymerisation of terpenes, showing a low softening point and a low VOC content. It is recommended to plasticize and to improve adhesion of pressure sensitive adhesives.

### TYPICAL VALUES

Dropping point, °C	20
--------------------	----

*DRT analytical methods are available on request*

### OTHER TECHNICAL DATA

Glass temperature (T <sub>g</sub> ), °C	-20
Viscosity at 80°C, mPa.s	150
Viscosity at 110°C, mPa.s	30
Viscosity at 150°C, mPa.s	15
Soluble in aromatic, aliphatic solvents	
Insoluble in alcohol and ketones	

### USES

Pressure sensitive adhesives (solvent based or Hot Melt based).

### TRANSPORT

HANDLING & STORAGE	Under cover and at temperature below 30°C
STABILITY	About 2 years storage conditions and inventory control must be observed.
PACKAGING	Metallic drums of 172 kg on pallet of 688 kg
CUSTOMS TARIFF	3911100090

### TECHNICAL DATA SHEET / 08.08.11

*The data herein are based on our knowledge about above product. They are without conditions or warranties, expressed or implied regarding the uses of the product.*

#### LES DÉRIVÉS RÉSINIQUES & TERPÉNIQUES

30 rue Gambetta - BP 206 - 40105 DAX Cedex - France  
www.drtr.fr - Tel. : +33 (0)5 58 56 62 00 - Fax : +33 (0)5 58 56 62 40

