

## DERCOLYTE S 115

Produced from the polymerisation of beta pinene, DERCOLYTE S 115 is a tackifying resin recommended to improve the adhesive properties (tack, adhesion) of solvent based adhesive formulations, particularly in PSA.

### TYPICAL VALUES

Softening point, Ring and Ball, °C	114
Gardner colour, 50 resin / 50 toluene	2
COV at 180°C, MG/KG	Max 300

*DRT analytical methods are available on request*

### OTHER TECHNICAL DATA

Transition glass temperature (Tg), °C	70
Molecular weight (Mw), g/mole	2 300
Soluble in aromatic, aliphatic solvents	
Insoluble in alcohol and ketones	

### USES

Solvent based PSA formulated with natural or acrylic rubber  
Hot Melt  
Mastic

### IDENTIFIERS

EINECS	Polymer. All monomers are listed
--------	----------------------------------

### TRANSPORT

HANDLING & STORAGE	Under cover and at temperature below 30°C
STABILITY	About 6 months in standard storage conditions. A strict inventory control must be observed.
PACKAGING	Flaked in 25 kg paper bags on wrapped pallets of 750 kg net weight. Big Bag of 1000 kg net weight.
CUSTOMS TARIFF	3911100090

### TECHNICAL DATA SHEET / 08.08.11

*The data herein are based on our knowledge about above product. They are without conditions or warranties, expressed or implied regarding the uses of the product.*

#### LES DÉRIVÉS RÉSINIQUES & TERPÉNIQUES

30 rue Gambetta - BP 206 - 40105 DAX Cedex - France  
www.drtr.fr - Tel. : +33 (0)5 58 56 62 00 - Fax : +33 (0)5 58 56 62 40

